What Is Claimed Is:

1. A method for continuously producing a metal laminate, comprising :

heat-treating a film comprising a thermoplastic polymer capable of forming an optically anisotropic melt phase on a heat treatment roll having unevenness on a surface thereof; and,

bonding a metal sheet to at least one side of the heat-treated film.

2. The method of producing the metal laminate according to Claim 1, wherein a thermal dimensional change of said heat-treated film is not more than 0.1% at 200°C.

3. The method of producing the metal laminate according to Claim 1, wherein the metal sheet is continuously bonded to at least one side of the film by thermal press-bonding.

4. The method of producing the metal laminate according to Claim 1, wherein the film is heat-treated on the heat treatment roll having the unevenness on the surface thereof under substantially no pressure.

5. The method of producing the metal laminate according to Claim 1, wherein a height of the unevenness provided on the surface of the heat treatment roll is within the range from 1 μm to 15 μm.

6. The method of producing the metal laminate according to Claim 1, wherein a temperature of the heat treatment roll is within the range from a temperature lower by 30°C than a thermal deflection temperature of the film to the thermal deflection temperature.